

## Formolene<sup>®</sup> 5140H

## Homopolymer for Compression Molded Caps and Closures

Formolene<sup>®</sup> 5140H is a polypropylene homopolymer with fast cycle time and easy mold release. It is designed for compression molded caps and closure applications. It contains a unique combination of stabilizers, nucleators and antistats that provide an excellent balance of stiffness and impact strength. Formolene<sup>®</sup> 5140 H offers advantages in both processing and physical properties over current polypropylenes used for compression molded caps and closures.

Formolene<sup>®</sup> 5140H meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Products" section on our website (http://www.fpcusa.com/ourproducts.html).

This material is free of animal-derived content.

## **Typical Properties of this Commercial Grade**

		Typical Values				
Property	Test Method	Eng	English		SI	
Melt Flow Rate, I <sub>2</sub> @ 230°C	ASTM D1238	2.1	g/10min	2.1	g/10min	
Density	ASTM D1505	0.9	g/cm3	0.9	g/cm <sup>3</sup>	
Tensile Strength at Yield (50 mm/min)	ASTM D638	5,400	psi	37	MPa	
Elongation at Yield (50 mm/min)	ASTM D638	5	%	5	%	
Flexural Modulus (1.3 mm/min), 1% Secant	ASTM D790	245,000	psi	1690	MPa	
Rockwell Hardness	ASTM D785	114	R Scale	114	R Scale	
Notched Izod Impact Strength @ 73°F	ASTM D256A	0.7	ft-lb/in	37	J/m	
Heat Deflection Temperature @ 66 psi	ASTM D648	243	°F	117	°C	

Note: Specimens were injection molded according to the conditions specified in ASTM D4101. Data for representative purposes only; not to be construed as product specification. Published 7/02, Revised 4/13

## Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 422-7772

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARKANTY OF ANY KIND, EXPRESS OR INPLIED, INCLUDING THOSS OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. Are cairms arising out of breach of warranty, regligence, strict liability or therwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.