

Formolene[®] 6550A

Impact Copolymer for Thin Walled Injection Molded Applications

Formolene[®] 6550A is a medium impact, high flow copolymer of polypropylene designed for such applications as housewares, containers and other rigid packaging. It is characterized by its easy mold flow, excellent physical property balance and finished product dimensional stability.

Formolene[®] 6550A meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Products" section on our website (<u>http://www.fpcusa.com/ourproducts.html</u>).

This material is free of animal-derived content.

Typical Properties of this Commercial Grade

| | | Typical Values | | | |
|---|-------------|----------------|-------------------|------|-------------------|
| Property | Test Method | English | | SI | |
| Melt Flow Rate, $I_2 @ 230^{\circ}C$ | ASTM D1238 | 50 | g/10 min | 50 | g/10 min |
| Density | ASTM D1505 | 0.9 | g/cm ³ | 0.9 | g/cm ³ |
| Tensile Strength at Yield (50 mm/min) | ASTM D638 | 3,000 | psi | 21 | MPa |
| Elongation at Yield (50 mm/min) | ASTM D638 | 5 | % | 5 | % |
| Flexural Modulus (1.3 mm/min), 1% Secant | ASTM D790 | 145,000 | psi | 1000 | MPa |
| Notched Izod Impact Strength @ 73°F | ASTM D256A | 1.7 | ft-lb/in | 91 | J/m |
| Heat Deflection Temperature @ 66 psi | ASTM D648 | 199 | °F | 93 | °C |
| Rockwell Hardness | ASTM D785 | 90 | R Scale | 90 | R Scale |

Note: Specimens were injection molded according to the conditions specified in ASTM D4101.

Data for representative purposes only; not to be construed as product specification. Published 2/09, Revised 3/18

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 422-7772

© Formosa Plastics Corporation, U.S.A.

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARKS NO WARKSNO WA