



Formolene® E900

High Molecular Weight High Density Polyethylene (HMW-HDPE) Bimodal Resin Designed For Non-Pressure Pipe Extrusion Applications

Formolene® E900 is a high molecular weight high density polyethylene (HMW-HDPE) resin designed for non-pressure pipe applications. Formolene® E900 is well balanced in overall physical properties and provides good stiffness for extrusion applications.

Suggested Applications:

- Corrugated Pipe
- Non-Pressure Pipe Extrusion Applications

Nominal Physical Properties:

PROPERTY	ASTM TEST METHOD	UNIT	VALUE
Density	D1505	g/cc	0.949
Melt Index,			
Condition E, 190°C/2.16 kg	D1238	g/10 min.	0.04
Condition F, 190°C/21.6 kg	D1238	g/10 min.	8.5
Tensile Strength at Yield, (50 mm/min)	D638	psi.	3,600
Tensile Elongation at Break, (50 mm/min)	D638	%	>600
Brittleness Temperature	D746	°F	<-180
Environmental Stress Crack Resistance, ESCR, Condition B			
10% Igepal	D1693	hrs.	>500
ESCR by NCTL @ 15% yield Stress	F2136	hrs.	400

The nominal properties reported herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification purposes.

Published 08/01/04, Revised 01/12/16

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 422-7772

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.