



Formosa Plastics®

Formolon® -260

PVC Homopolymer Blending Resin

F-260 is a fine particle size PVC homopolymer plastisol blending resin. It combines excellent fusion characteristics, low plastisol viscosities as well as lot to lot uniformity. In combination with dispersion resin, F-260 has been successfully used in top coats, chemically blown foam, and various molding processes.

TYPICAL RESIN PROPERTIES

Relative Viscosity	ASTM D2857	2.10
Inherent Viscosity	ASTM D1243	0.87
K-Value	Fikentscher's Constant	63
Bulk Density	ASTM D1895 (A)	0.57 g/cc
Volatiles	ASTM D3030	0.5%
Sieve Analysis	ASTM D1921(B)	
Through 40 Mesh Screen		100 %
Through 200 Mesh Screen		99 %
Average Particle Size	Coulter Counter LS230	35 micron

NOTE: The physical data presented above are typical values and should not be construed as a specification.

Originally Published 04/01/2002, Revised 09/06/2019.

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (800) 363-1823 • Fax: (973) 716-7483

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.