



Formosa Plastics®

Formolene® FC3403C

Clarity LDPE Resin with no Slip or Antiblock

Formolene® FC3403C is a low density polyethylene offering good balance of optical properties and high stiffness.

Formolene® FC3403C is formulated without slip and antiblock for use in applications offering excellent extrusion processing and good balance of film stiffness and optical properties.

Suggested Applications:

Cast Film
Co-Extrusion Films
Embossed Films

Hygiene Packaging
Label Film
Overwrap Film

Paper Overwrap

Nominal Physical Properties:

PROPERTY	TEST METHOD	UNIT	VALUE
Density	D792	g/cc	0.934
Melt Index, Condition E, 190°C/2.16 kg	D1238	g/10 min	3.0
Dart Impact	D1709	g	60
Elmendorf Tear Strength	D1922	g	100/170*
Tensile Strength at Yield	D882	psi	2200/2200*
Tensile Strength at Break	D882	psi	3200/2600*
Elongation at Break	D882	%	430/560*
Secant Modulus @ 1%	D882	psi	54000/54000*
Gloss (45°)	D2457		73
Haze	D1003	%	6.0

* MD / TD

Note: Film properties based on 1.18 mil (30 micron) thick film using a 7.9 in (200 mm) blown film line with a 2.5:1 blow-up ratio, a melt temperature of 284 - 338°F (140 - 170°C), a 39.4 mil (1.0 mm) die gap. Actual film properties may vary based on extrusion equipment, operating conditions and additive package. Film properties are not intended to be used as specifications.

Published 07/15/19

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (800) 363-1823 • Fax: (973) 716-7483

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.