

## Formolene<sup>®</sup> FE2306

## LDPE Resin with no Slip or Antiblock

Formolene<sup>®</sup> FE2306 is a low density polyethylene offering good stiffness and good toughness. Formolene<sup>®</sup> FE2306 is formulated without slip and antiblock for use in applications offering easy processing.

Formolene<sup>®</sup> FE2306 meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

## **Suggested Applications:**

| Compounding    | Houseware Articles |
|----------------|--------------------|
| Food Packaging | Injection Molding  |

Masterbatch Base Resin Rigid Medium Sized Molding

## **Nominal Physical Properties:**

|  | TEST            |          |        |
|--|-----------------|----------|--------|
| PROPERTY                               | METHOD          | UNIT     | VALUE  |
| Density                                | D792            | g/cc     | 0.923  |
| Melt Index, Condition E, 190°C/2.16 kg | D1238           | g/10 min | 6.5    |
| Vicat Softening Temperature            | ISO 306         | °F/°C    | 194/90 |
| Tensile Modulus                        | ISO 527-2/1A/1  | psi      | 23000  |
| Tensile Stress (100% Strain)           | ISO 527-2/1A/50 | psi      | 1400   |
| Shore Hardness (Shore D, 15 sec)       | ISO 868         |          | 45     |

Note: The molded properties were measured on 157.5 mil (4 mm) thick injection molded specimen based on ISO 1872-2. Typical properties are not intended to be used as specifications. Published 10/20/2024

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However because of numerous factors affecting results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

© Formosa Plastics Corporation, U.S.A.