



Formosa Plastics®

Formolene® FR2375D

Fractional Melt LDPE Resin with 500 ppm Slip and 450 ppm Antiblock

Formolene® FR2375D is a low density polyethylene with films exhibiting good mechanical and optical properties in blends.

Formolene® FR2375D is formulated with slip and antiblock for use in film applications offering excellent extrusion processing and very good balance of mechanical and optical properties.

Suggested Applications:

Agricultural Film	Collation Shrink	Medium Duty Shrink Film
Blend Partner	Freezer Film	Shoppers
Co-Extrusion Films	Lamination Film	Form Fill and Seal Packaging

Nominal Physical Properties:

PROPERTY	TEST METHOD	UNIT	VALUE
Density	D1505	g/cc	0.923
Melt Index, Condition E, 190°C/2.16 kg	D1238	g/10 min	0.75
Dart Impact	D1709	g	180
Elmendorf Tear Strength	D1922	g	350/150*
Tensile Strength at Break	D882	psi	4000/3200*
Elongation at Break	D882	%	310/530*
Secant Modulus @ 1%	D882	psi	35000/40000*
Gloss (45°)	D2457		59
Haze	D1003	%	8.4

* MD / TD

Note: Film properties based on 1.97 mil (50 micron) thick film produced using a 7.9 inch (200 mm) die and 39.4 mil (1.0 mm) die gap with a 2.5:1 Blow-Up Ratio and temperature profile of 356 - 374° F (180 - 190°C). Actual film properties may vary based on extrusion equipment, operating conditions and additive package. Film properties are not intended to be used as specifications.

Published 07/15/19

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (800) 363-1823 • Fax: (973) 716-7483

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.