



Formosa Plastics®

Formolene Formax® L92005H

High Strength Linear Low Density Polyethylene for Film Extrusion Applications

Formolene FORMAX® L9 is a high strength linear low-density polyethylene. Film mechanical properties are significantly improved compared to competitive super hexene LLDPE film resins.

Formolene FORMAX® L9 can be formulated with slip, antiblock, PPA, and AO for use in high performance film applications offering excellent extrusion processing and outstanding impact strength and tear resistance. Films exhibit superior sealing characteristics and good optical properties.

Formolene FORMAX® L9 meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

Suggested Applications:

Industrial Packaging	Industrial Liners	Food Packaging
Can Liners	Consumer Trash Bags	Coextrusion

Nominal Physical Properties:

PROPERTY	TEST METHOD	UNIT	VALUE
Density	D1505	g/cc	0.920
Melt Index, Condition E, 190°C/2.16 kg	D1238	g/10 min	0.50
Dart Impact	D1709	g	250
Tear Strength	D1922	g	500/650*
Yield Strength	D882	psi	1550/1550*
Tensile Strength at Break	D882	psi	9000/7000*
Elongation at Break	D882	%	650/800*

* MD / TD

Available in the following additive packages:

Additive	L92005H
Antiblock (ppm)	No
Slip (ppm)	No
Special	High AO

Note: Film properties based on 25 micron blown film produced with a 2.5:1 Blow Up Ratio at 12 lbs/hr/in.die. Actual film properties may vary based on extrusion equipment, operating conditions and additive package. Film properties are not intended to be used as specifications.

Published 11/23

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However because of numerous factors affecting results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

© Formosa Plastics Corporation, U.S.A.

Formolene® & Formolon® are registered trademarks of FPC USA