



Formolene® HL5010

Extra High Molecular Weight Hexene Copolymer

Formolene® HL5010 has good melt strength, excellent stress crack resistance, good rigidity, and excellent impact strength even at low temperatures. These properties make Formolene® HL5010 an excellent resin for large part blow molding applications.

Formolene® HL5010 meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520 for food packaging, covering safe use of polyolefin articles intended for direct food contact.

Suggested Applications:

Blow Molded...

55-Gallon Shipping Containers

Gasoline Tanks

Agricultural Chemical Tanks

Extruded...

Pallets

Large Formed Parts

Corrugated Pipes (Certified to AASHTO M294)

Conduit Pipes (Meets ASTM F2160)

Nominal Physical Properties:

PROPERTY*	ASTM TEST METHOD	English		SI	
		UNIT	VALUE	UNIT	VALUE
Density	D1505	g/cc	0.948	g/cc	0.948
Melt Index, Condition E, 190°C/21.6 kg (HLMI)	D1238	g/10 min	10.0	g/10 min	10.0
Environmental Stress Crack Resistance (ESCR) Condition B, F ₅₀ (100% Igepal)	D1693	h	>1000	h	>1000
Tensile Yield Strength 2" (50 mm) per min.	D638 Type IV	psi.	3600	MPa	25
Ultimate Elongation 2" (50 mm) per min.	D638 Type IV	%	>600	%	>600
Brittleness Temperature	D746	°F	<-131	°C	<-91
Flexural Modulus	D790	psi.	170,000	MPa	1172

* Physical properties reported herein were determined on compression molded specimens prepared in accordance with Procedure C of ASTM D4703, Annex A1.

The nominal properties reported herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification purposes.

Published 06/01/01, Revised 06//2022

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However because of numerous factors affecting results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.