



Formolene® HL3721

Medium Density Polyethylene

Formolene® HL3721 is a high molecular weight hexene copolymer resin tailored specifically for cast extrusion production of geomembrane films. The resin provides an excellent balance of ESCR properties, broad fusion range, excellent melt strength and good overall processability.

Suggested Applications:

Landfill Liners	Gasoline and Chemical Tank Containment Liners
Tunnel Moisture Barriers	Mine Tailing Collection Projects

Nominal Physical Properties:

PROPERTY*	ASTM TEST METHOD	ENGLISH		SI	
		Unit	Value	Unit	Value
Density	D1505	g/cc	0.937	g/cc	0.937
Melt Index, Condition E, 190°C/21.6 kg (HLMI)	D1238	g/10 min.	21.0	g/10 min.	21.0
Tensile Yield Strength 2 in. per min., Type IV bar	D638	psi.	2,900	MPa	20
Elongation at Break 2 in. per min., Type IV bar	D638	%	800	%	800
Flexural Modulus, Tangent – 16:1 span:depth, 0.5 in./min.	D790	psi.	120,000	MPa	830
ESCR Condition B (10% Igepal), F ₅₀	D1693	h	>1,500	h	>1,500
Condition C (100% Igepal), F ₅₀	D1693	h	>1,500	h	>1,500
SP-NCTL	D5397	h	>900	h	>900
Durometer Hardness, Type D (Shore D)	D2240	Shore D	57	Shore D	57
Vicat Softening Temperature, Loading 1, Rate A	D648	° F	221	° C	105
Heat Deflection Temperature, 66 psi., Method A	D648	° F	137	° C	58
Brittleness Temperature, Type A, Type I specimen	D746	° F	<-103	° C	<-75
Tensile Impact Type S Bar	D1822	ft-lb/in ²	190	KJ/m ²	400

*The nominal properties reported herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification purposes.

Published 7/16, Revised 1/18

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 422-7772

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.