



**Formosa Plastics®**

## 6530N<sup>®</sup> ( ISO Format )

### **Impact Copolymer - Designed to Meet Above the Shoulder Requirements of Automotive Interiors.**

Formolene<sup>®</sup> 6530N is a high impact, copolymer polypropylene. It was specifically developed to meet the OEM requirements for automotive interior door panels used for above shoulder applications.

Material has been approved under Renault-Nissan AS3.

This material is free of animal-derived content.

#### **Typical Properties of this Commercial Grade**

Property	Test Method	Typical Values			
		English		SI	
Melt Flow Rate, I <sub>2</sub> @ 230°C	ISO 1133	25	g/10min	25	g/10 min
Density	ISO 1183	0.9	g/cm <sup>3</sup>	0.9	g/cm <sup>3</sup>
Tensile Strength at Yield (50 mm/min)	ISO R527	2750	psi	19	MPa
Elongation at Yield (50 mm/min)	ISO R527	5	%	5	%
Flexural Modulus (1.3 mm/min), 1% Secant	ISO 178	140	Kpsi	970	MPa
Notched Izod Impact Strength @ 23°C	ISO 180	6.5	ft-lb/in	43	KJ/m <sup>2</sup>
Notched Izod Impact Strength @ -30°C	ISO 180	1.5	ft-lb/in	9.5	KJ/m <sup>2</sup>
Notched Izod Impact Strength @ -40°C	ISO 180	1.2	ft-lb/in	8.0	KJ/m <sup>2</sup>
Charpy Impact @ 23 °C	ISO 179	7.5	ft-lb/in	50	KJ/m <sup>2</sup>
Charpy Impact @ -30 °C	ISO 179	1.2	ft-lb/in	8.0	KJ/m <sup>2</sup>
Charpy Impact @ -40°C	ISO 179	1.0	ft-lb/in	7.0	KJ/m <sup>2</sup>
Heat Deflection Temperature @ 264 psi, (Ae)	ISO 75	120	°F	49	°C
Heat Deflection Temperature @ 66 psi, (Be)	ISO 75	188	°F	87	°C

*Notes: Specimens were injection molded according to the conditions specified in ASTM D4101  
Data for representative purposes only; not to be construed as product specification. Published 04 20*

**Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (800) 363-1823 • Fax: (973) 716-7483**

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However because of numerous factors affecting results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.